

NUMBER :VNMT20006899



Intertek Vietnam Ltd.

TEST REPORT**NUMBER : VNMT20006899****DATE : 27-Feb-2020**

APPLICANT : CONG TY TNHH-SX-TM-DV THAO MINH
2977/11 HIGHWAY 1A, SECTOR 5, TAN THOI NHAT WARD,
DISTRICT 12, HO CHI MINH, VIET NAM

ATTN : KHUONG

Sample Description As Declared : Face Mask
Color : White
No. of Sample : 2 Pieces + Fabric
Order No./PO No. : -
Buyer Name : -
Style No. : -
Fiber Content : -
Article No. : -
Date Received/Date Test Started : 25 Feb 2020
Date Confirmation Received : -

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE REFER TO ENCLOSED PAGE(S)

AUTHORIZED BY
FOR INTERTEK VIETNAM LTD. [HO CHI MINH]



PHUONG LE
SOFTLINES GENERAL MANAGER

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.

Page 1 of 3

Hochiminh office: 5th,6th,7th floor, Lobby D, S.O.H.O Biz Office Building, No. 38 Huynh Lan Khanh St., Ward 2, Tan Binh District, Ho Chi Minh City, Vietnam. Tel: (84-28) 62971099
62971098 Email: consumergoods.vietnam@intertek.com

Fax: (84-28)

Hanoi office:3rd floor, Au Viet Building, No.01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi, Vietnam. Tel:(84-24)37337094 Fax:(84-24)37337093 Website:www.intertek.com

TEST REPORT**NUMBER : VNMT20006899****DATE : 27-Feb-2020**

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. Water Repellency - As Received

ISO 4920 - 2012

Rating 4.5*

REMARK:

*Water Penetration Through From Face To Back (Shell Fabric)

2. Transmittance or Blocking of Erythemally Weighted Ultraviolet Radiation Through Fabric

AATCC 183 - 2014 , ASTM D6603-2019 (As Received Only)

- Solar Spectrum Irradiance Used: Noonday, July 3, Sunlight, Albuquerque

- Instrument Used: UV-2000F

- Wavelength Resolution: 2 nm

- No. of Scan: 6

	Shell	
	<u>Dry</u>	<u>Wet</u>
The Mean Ultraviolet Protection Factor, UPF	24.0	28.23
The UV-A Transmittance, T(UV-A)	6.19%	5.88%
The UV-B Transmittance, T(UV-B)	3.58%	2.94%
The Percent Blocking (UV-A)	93.81%	94.12%
The Percent Blocking (UV-B)	96.42%	97.06%
UPF Rating For Label	20	20
UVR Protection Category	Good Protection	Good Protection
	Lining	
	<u>Dry</u>	<u>Wet</u>
The Mean Ultraviolet Protection Factor, UPF	71.15	21.94
The UV-A Transmittance, T(UV-A)	0.90%	1.99%
The UV-B Transmittance, T(UV-B)	1.16%	3.61%
The Percent Blocking (UV-A)	99.10%	98.01%
The Percent Blocking (UV-B)	98.84%	96.39%
UPF Rating For Label	20	20
UVR Protection Category	Good Protection	Good Protection

END OF THE TEST REPORT

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.

Page 2 of 3

Hochiminh office: 5th,6th,7th floor, Lobby D, S.O.H.O Biz Office Building, No. 38 Huynh Lan Khanh St., Ward 2, Tan Binh District, Ho Chi Minh City, Vietnam. Tel: (84-28) 62971099
62971098 Email: consumergoods.vietnam@intertek.com

Fax: (84-28)

Hanoi office:3rd floor, Au Viet Building, No.01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi, Vietnam. Tel:(84-24)37337094 Fax:(84-24)37337093 Website:www.intertek.com

TEST REPORT**NUMBER : VNMT20006899****DATE : 27-Feb-2020**

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>.

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

Intertek Vietnam Ltd.

Page 3 of 3

Hochiminh office: 5th,6th,7th floor, Lobby D, S.O.H.O Biz Office Building, No. 38 Huynh Lan Khanh St., Ward 2, Tan Binh District, Ho Chi Minh City, Vietnam. Tel: (84-28) 62971099
62971098 Email: consumergoods.vietnam@intertek.com

Fax: (84-28)

Hanoi office:3rd floor, Au Viet Building, No.01 Le Duc Tho Street, Mai Dich Ward, Cau Giay District, Hanoi, Vietnam. Tel:(84-24)37337094 Fax:(84-24)37337093 Website:www.intertek.com